

APPROXIMATE INTERNATIONAL EQUIVALENTS OF SOME OF THE MORE COMMON TYPES OF STAINLESS STEEL

OLD* EN NOS.	USA RSA	UNITED KINGDOM *	GERMANY * WERKSTOFF	DIN	FRANCE *	SWEDEN *	ITALY * UNI	JAPAN JIS	EURONORM *
58 A	201	284 S 16	1,4371	X 12 CrMnNi 18 8 5				SUS 201	
	01	301 S 21	1,4310	X 12 CrNi 17 7	Z 12CN 17-08	14 2331	X 12 CRNi 1707	SUS 301	X 9 CrNi 18-8
58 M	302	302 S 25	1,4300	X 12 CrNi 18 8	Z 10CN 18-08	14 23321	X 12 CrNi 1809	SUS 302	
	303	303 S 22	1,4305	X 10 CrNiS 18 9	Z 10CNF 18-09				X 8 CrNiS 18-9
58 E	303Se	303 S 41			Z 10CNF 18-09	14 2346	X 10 CrNiS 1809		
	304	304 S 15	1,4301	X 5 CrNi 18 10	Z6CN 18-09	14 2333	X 5 CrNi 1810	SUS 304	X 4 CrNi 18-10
	304L	304 S 11	1,4306	X 2 CrNi 19 11	Z2CN 18-10	14 2352	X 2 CrNi 1811	SUS 304L	X 2 CrNi 19-11
	305		1,4312		Z 8CN 18-12				
	309	309 S 24	1,4828		Z15CN 24-13		X16 CrNi 2314		
	309S								
	310	310 S 24	1,4841		Z12CN 25-20	14 2361	X 6 CrNi 2520		
	310S		1,4845			14 2361	X 6 CrNi 2520		
58 S	316	316 S 31	1,4401	X 5 CrNiMo 17 12 2	Z6CND 17-11	14 2343	X8 CrNiMo 1713	SUS 316	X4 CrNiMo 17-12-2
	316L	316 S 11	1,4435	X2 CrNiMo 18 14 3	Z2CND 17-12	14 2348	X 2 CrNiMo 1712	SUS 316L	X 2 CrNiMo 18-14-3
	316Ti	320 S 31				14 2350			
58 C	317	317 S 16	1,4436	X 5 CrNiMo 17 13 3				SUS 317	X 4 CrNiMo 17-13-3
	321	321 S 31	1,4541	X 6 CrNiTi 18 10	Z6CNT 18-12	14 2337	X 6 CrNiTi 1811	SUS 321	X 6 CrNiTi 18-10
58 G	347	347 S 31	1,4550	X 6 CrNiNb 18 10	Z6CNNb 18-11	14 2338	X8 CrNiNb1811	SUS 347	X6CrNiNb 18-10
	348								
	403	403 S 17	1,4024	X 15 CrI 3	Z 12 C 13	14 2301		SUS 403	X 15 CrI3
	405	405 S 17	1,4002	X 6 CrAl 13	Z6CA 13		X 6 CrAl 13	SUS 405	X 6 CrAl 13
	409	409 S 19	1,4512	X6 CrTi 12					X 2 CrTi 12
56 A	410	410 S 21	1,4006	X 10 Cr 13	Z 12C 13	14 2302	X 120 -13	SUS 410	X 12Cr13
56 AM	416	416 S 21	1,4005	X 12 CrS 13			X 12 CrS 13		
56 D	420	420 S 45	1,4021	X 20 Cr 13	Z 20C 13	14 2304	X 30 Cr13	SUS 420JI	X 20 Cr 13
60	430	430 S 17	1,4016	X 6 Cr 17	Z 8C 17	14 2320	X 8 Cr 17	SUS 430	X6 Cr 17
	430F		1,4104	X 12 CrMoS 17	Z 10CF 17	14 2383	X 10 CrS 17	SUS 430F	
57	431	431	1,4057	X 20 CrNi 17 2	Z 15CN 16-02	14 2321	X 16 CrNi 16	SUS 431	
			1,4462	X 2 CrNiMoN 22 5 3	Z 2CND 22-05-03	14 2337			
			1,4362	X 2 CrNiM 23 4	Z 2 CN 23-04 AZ	14 2327			X 2 CrNiN 23-4